
Amendment to the Claims:

This listing of claims will replace all prior versions and listings of claims in the application:

 (Currently Amended) A process for the preparation of a hydrogenated nitrile rubber comprising reacting a nitrile rubber in the presence of hydrogen, optionally at least one co-olefin, and in the presence of at least one compound selected from the group consisting of compounds of the general formula I,



Formula I

wherein

M is Os or Ru,

R and R¹ are, independently, hydrogen or a hydrocarbon selected from the group consisting of C₂-C₂₀ alkenyl, C₂-C₂₀ alkynyl, C₁-C₂₀ alkyl, aryl, C₁-C₂₀ carboxylate, C₁-C₂₀ alkoxy, C₂-C₂₀ alkenyloxy, C₂-C₂₀ alkynyloxy, aryloxy, C₂-C₂₀ alkoxycarbonyl, C₁-C₂₀ alkylthio, C₁-C₂₀ alkylsulfonyl and C₁-C₂₀ alkylsulfinyl,

X and X¹ are independently any anionic ligand,

L is any neutral ligand

L' is selected from any 1-3 disubstituted imidazolidinylidene or 1,3 disubstituted imidazolidine ligand,

wherein a metathesis reaction and a hydrogenation reaction occur simultaneously.

2. (Original) A process according to claim 1 wherein the process occurs in the absence of any co-olefin.

CH-8312 2

- 3. (Currently Amended) A process according to claim [[3]] 1 wherein either L is a trialkylphosphine and L¹ is an imidazolidinylidene, X and X¹ are chloride ions and M is ruthenium.
- 4. (Currently Amended) A process according to <u>claim 1</u> any of claims 1-4 wherein the ratio of compound to nitrile rubber is in the range of from 0.005 to 5.
- 5. (Currently Amended) A process according to any of claims claim 1[[-5]] wherein the process is carried out in an inert solvent selected from the group consisting of monochlorobenzene, dichloromethane, benzene, toluene, tetrahydrofuran and cyclohexane.

CH-8312 3